


Pannelli copertura
in poliuretano


Roof panels with polyurethane insulation

Dachpaneele, isoliert mit PU-Hartschaum


Panneaux de couverture avec isolation en mousse polyuréthane



PARTICOLARE DEL GIUNTO



- Spessore (mm)
- Thickness
- Plattenstärke
- Epaisseur



Spessore Pannello (mm)	Trasmittanza Termica in Accordo UNI EN 14509 A.10 U (W/m ² K)	Coefficiente di Trasmissione Termica Medio Iniziale in Accordo EN ISO 6946 K (W/m ² K)
30	0,73	0,55
40	0,56	0,44
50	0,45	0,36
60	0,38	0,31
80	0,28	0,24
100	0,23	0,20
120	0,19	0,17
150	0,15	0,13

DISEGNO TECNICO PENTA

