

Tabella del peso - ACCIAIO per CEMENTO ARMATO									
Ø mm.	Peso kg./ml.	Sezione in Cm <sup>2</sup> per N. di barre							
		1	2	3	4	5	6	8	10
6	0,222	0,28	0,57	0,85	1,13	1,41	1,70	2,26	2,83
7	0,302	0,38	0,77	1,16	1,54	1,93	2,31	3,08	3,85
8	0,395	0,50	1,01	1,51	2,01	2,52	3,02	4,02	5,03
9	0,499	0,64	1,27	1,91	2,54	3,18	3,82	5,09	6,36
10	0,617	0,79	1,57	2,36	3,14	3,93	4,71	6,28	7,85
11	0,746	0,95	1,90	2,85	3,80	4,75	5,70	7,60	9,50
12	0,888	1,13	2,26	3,39	4,52	5,65	6,78	9,04	11,30
14	1,208	1,54	3,08	4,62	6,16	7,70	9,24	12,32	15,40
16	1,578	2,01	4,02	6,03	8,04	10,05	12,06	16,08	20,10
18	1,998	2,54	5,08	7,62	10,16	12,70	15,24	20,32	25,40
20	2,466	3,14	6,28	9,42	12,56	15,70	18,84	25,12	31,40
22	2,984	3,80	7,60	11,40	15,20	19,01	22,80	30,40	38,00
24	3,551	4,52	9,04	13,56	18,08	22,60	27,12	36,16	45,20
26	4,168	5,31	10,62	15,93	21,24	26,55	31,86	42,48	53,10
28	4,834	6,16	12,32	18,48	24,64	30,80	36,96	49,28	61,60
30	5,549	7,07	14,14	21,21	28,28	35,35	42,42	56,56	70,70
32	6,313	8,04	16,08	24,12	32,17	40,21	48,25	64,33	80,42
34	7,127	9,08	18,16	27,24	36,32	45,40	54,48	72,63	90,79
36	7,990	10,18	20,36	30,54	40,72	50,90	61,07	81,43	101,79
38	8,903	11,34	22,68	34,02	45,36	56,71	68,05	90,73	113,41
40	9,865	12,57	25,13	37,70	50,26	62,83	75,40	100,53	125,66

